

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C25B 11/00, C23C 18/08	A1	(11) International Publication Number: WO 99/02762 (43) International Publication Date: 21 January 1999 (21.01.99)
(21) International Application Number: PCT/EP98/04270 (22) International Filing Date: 9 July 1998 (09.07.98) (30) Priority Data: MI97A01643 10 July 1997 (10.07.97) IT (71) Applicant (for all designated States except US): DE NORA S.P.A. [IT/IT]; Via Bistolfi, 35, I-20134 Milan (IT). (72) Inventors; and (75) Inventors/Applicants (for US only): MANTEGAZZA, Claudio [IT/IT]; Via Miola, 64, I-21047 Saronno (IT). ZIONI, Emilio [IT/IT]; Via Arno, 6, I-20090 Trezzano sul Naviglio (IT). (74) Agents: KINZEBACH, Werner et al.; Reitsötter, Kinzebach & Partner, Postfach 86 06 49, D-81633 München (DE).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: METHOD FOR APPLYING A COATING TO A METAL SUBSTRATE OR REPAIRING A COATING APPLIED TO THE SAME (57) Abstract The invention describes a method for applying an electrocatalytic or a protective coating to a metal substrate or repairing a damaged area of the same, consisting in a thermal treatment of a precursor of said catalytic coating by means of a hot air jet from a blower. The temperature of the substrate is locally controlled by means of surface temperature sensors or by an infrared measuring system. The metal substrate may be an exhausted electrode structure, in which case the reactivation is easily carried out at the plant site without any need of sending the structure to the producer. The method of the invention is particularly useful for reactivating anodes for oxygen evolution as it permits to avoid the risky procedure of detaching the anode from the current conductor.		

hot
air

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

METHOD FOR APPLYING A COATING TO A METAL SUBSTRATE OR
REPAIRING A COATING APPLIED TO THE SAME

The use of electrodes obtained by coating a valve metal substrate (for example titanium, zirconium, niobium, tantalum) with an electrocatalytic paint is known for use in different application fields. These electrodes may be useful in several electrolytic processes, for example for the evolution of chlorine from sodium chloride brine, as anodes for oxygen evolution in electrometallurgical processes or anodes for cathodic protection.

U.S. patent no. 3,632,498 describes a general method for the production of this type of electrodes, which consists in applying to the valve metal a precursor, that is a paint containing the electrocatalytic components in ionic form, which is converted into the catalyst by means of a thermal treatment in air (activation). The temperatures required for the conversion may be extremely high (300-800°C). The most common method for the industrial production of these electrodes foresees, after the application of each paint layer, heating in oven at high temperature. As these electrodes usually have a very large size, the ovens have a great thermal mass which involves high production costs and severe problems due to the need of maintaining a homogeneous temperature profile throughout the whole volume. The electrodes usually comprise a frame for anchoring to the electrochemical cells wherein they are to be used. During heating in oven it is the whole electrode structure that undergoes the thermal treatment with the consequent waste of the energy used to heat unnecessarily the frame of the electrode. However, the most severe disadvantage is represented by the distortions caused by said treatment to some particularly critical areas, such as welding and connection points

among different parts. Electrodes with a thin layer of a catalyst which coats the valve metal offer the main advantage that at the end of the active lifetime there is no need for substituting the electrode but just providing for reactivation with a new catalytic paint, as described in British Patent No. 1.324.924.

The application of the coating is a simple procedure carried out by spraying, which could be made even at the plant site if it were not necessary to resort to large dimensions ovens capable of reaching the necessary high temperatures, a burden which most users cannot bear, also due to the fact that a large number of elements should be treated in order to justify the oven installation and operation costs. Therefore the exhausted electrodes are usually returned to the producers to be reactivated, with remarkable additional costs for shipping and packing of the same.

In many cases re-inserting the electrode into the production cycle requires further steps. This is the case, for example, with the anodes for oxygen evolution used in some electrometallurgical processes where it is extremely important that the whole surface operate at the same potential and where the ohmic drops of the electrode structure should be kept at very low values. For this reason a current conducting structure is welded onto the active surface of the electrode, which conductive structure consists of a metal having good conductive properties, for example, copper coated with a valve metal. In order to reactivate this type of electrodes, usually the current conductive structure must be detached, as it cannot undergo the thermal decomposition treatment at high temperature, due to the different expansion characteristics of the two metals. A high

number of elements are severely damaged during the detachment and must be substituted. Further, welding of the current conductive structure to the electrode involves a strong risk of locally damaging the catalyst and must be carried out with particular care by highly qualified technicians.

The application of paint onto a metal surface is not limited to the case of electrodes. A particular case is the application of catalytic paints to valve metals, as described in U.S. patents Nos. 4,082,900 and 4,154,897. These patents describe the application of a paint containing a first oxide of an element of the platinum group and a second oxide having special characteristics to inhibit corrosion. This type of coating is particularly useful for protecting localized areas, for example interstices and junctions where crevice corrosion could destroy the integrity of the element. As the thermal treatment is required only in these localized areas, the need to subject the whole element to a thermal treatment in oven strongly penalizes said application both under the economical and practical standpoints.

It is the main object of the present invention to overcome the prior art shortcomings by providing a method for applying an electrocatalytic or protective coating to a metal substrate comprising applying a precursor of said electrocatalytic or protective coating material to the surface of said metal substrate and subjecting the surface to a local thermal treatment by a hot air gun or blower to produce high temperature and keep it under continuous control. The control of the temperature of the metal substrate is made locally by means of surface temperature sensors or by means of infrared measuring systems.

The dimension of the surface heated by the air jet depends on the type of nozzle applied to the blower and may vary from some square centimeters to some hundred square centimeters.

It is a particular object of the invention to provide a method for applying an electrocatalytic coating onto a substrate, which may consist of an exhausted electrode and which may be carried out at the plant site without any need for shipping the exhausted electrode structure to the producers. The method of the invention is particularly useful for reactivating anodes for oxygen evolution as it permits to avoid the risky operation of detaching the current conducting structure.

It is another object of the invention to provide a method not only for reactivating exhausted electrodes but also for treating new electrodes and elements which need a protective coating against corrosion, whereas flanges or gaskets are applied during assembling in the plant. It is a further object to provide a method for repairing a damaged area of a metal substrate, previously provided with a coating..

The invention will be better illustrated by means of some examples, which are not to be intended as a limitation of the same.

EXAMPLE 1

A solution made of :

- 620 ml n-butanol
- 40 ml HCl 36%
- 300 ml butyl titanate
- 100 g RuCl_3

was applied by electrostatic brushing to a titanium electrode structure having an active surface of 1 m^2 , upon hot pickling in oxalic acid, cleaning in a ultrasonic bath and drying.

After each application of the paint, the electrode surface was heated by an air jet at 500°C from a Leister blower, "Robust" 7.5 kW type, provided with a rectangular nozzle, 30 cm long and 1 cm wide. The treatment lasted about one hour and the temperature of the metal substrate was kept under control by an infrared system for local measurement.

The electrode thus prepared was used as an anode for the electrolysis of sodium chloride in a mercury cathode cell fed with 28% brine at a pH of 2.5 and a temperature of 80°C . The cell was inserted in an industrial circuit of cells equipped with commercial electrodes. The current density was 10 kA/m^2 ; the overvoltage of the electrode of the invention showed no significant difference with respect to the commercial electrodes.

EXAMPLE 2

Two zirconium bars having the same size were degreased and pickled for 8 hours in a 10% oxalic acid solution at 90°C . A paint having the following composition was then applied to the bars :

- 30 ml TiCl_3 dissolved in water
- 3 g anhydrous FeCl_3
- 1 g FeCl_2

The first bar was subjected to thermal treatment in oven at a temperature of 600°C for 2 hours. The second bar was subjected to a thermal treatment according to the method of the invention with a hot air jet at 600°C using the same blower of Example 1, for about one hour, the only exception being the use of thermocouples to measure the temperature.

Each bar was connected to a cathodic protection system of steel structures buried in the soil and both bars correctly performed for above 1000 hours at a current density of 1000 A/m².

EXAMPLE 3

The titanium anodic flange of a bipolar element of a De Nora DD 350 membrane electrolyzer, potentially subject to crevice corrosion phenomena, was painted in three subsequent applications with a solution made of :

- 3 g RuCl₃
- 1.74 g H₂IrCl₆
- 390 mg TiCl₃ from a 4% by weight hydrochloric acid solution
- 1 ml 2-propanol

After each application, only the painted portion was subjected to the thermal treatment according to the method of the invention with a hot air jet at 540°C using the same blower of Example 1, for 25 minutes, the temperature of the metal substrate being kept under control by means of an infrared system for local measurement.

The element comprising the flange thus treated was inserted and operated in an experimental bipolar De Nora DD 350 electrolyzer comprising a second element, the anodic flange of which had not been subjected to any treatment against corrosion. After 3000 hours of operation the element protected by the catalytic paint did not show any corrosion phenomena. The anodic flange of the un-treated element appeared to be covered in localized areas by a pulverulent deposit which, from a chemical analysis, resulted to be essentially made of TiO₂.

EXAMPLE 4

The damaged coating of a flange of a bipolar element of a DD 350 electrolyzer was repaired as described hereinafter. The bipolar element came from an industrial electrolyzer disassembled after three years of operation for the substitution of a membrane. During the detachment of the gaskets, the protective coating of the titanium flange of one bipolar element came off in a limited corner area. After careful washing with demi water and drying, the damaged area was ground with corindone sand removing also a small quantity of the old coating along the periphery. After another washing and drying, the ground area was treated as described in Example 3. The new coating successfully overcome the adherence test carried out by applying a suitable scotch tape and then tearing it off. No appreciable amounts of coating were removed.

EXAMPLE 5

An anode for oxygen evolution, made of a titanium base activated by a catalytic coating and a current conducting structure made of copper coated with titanium and directed to minimizing the ohmic drops and therefore to keep the electrochemical potential of the anode uniform, was used in chromium plating processes and withdrawn at the end of the lifetime, degreased, sandblasted and pickled in a sulphuric acid solution. The anode was then reactivated according to the following procedure:

- four repeated applications of a mixture made of

100 mg/ml TaCl_5

150 mg/ml $\text{IrCl}_3 \cdot 3\text{H}_2\text{O}$

in a 20% hydrochloric acid solution up to obtaining a deposit of 1 g/m^2
of noble metal

- drying at 150°C and thermal decomposition at 500°C, after each application of the above paint, by means of a hot air jet using the same blower of Example 1.

The electrode was re-inserted in the chromium plating bath, made of 300 g/l of CrO_3 and 4 g/l of H_2SO_4 , wherein it worked continuously for 1500 hours with the same electrochemical performances as before deactivation.

The invention has been described making reference to specific embodiments thereof. However, it must be understood that modifications of the same are possible without departing from the spirit and scope of this invention. One with ordinary skill can make various changes and modifications to this invention to adapt it to the various uses and conditions. As such, these changes and modifications are properly, equitably and intended to be within the full range of equivalents of the following claims.

CLAIMS

1. A method for applying an electrocatalytic or protective coating to a metal substrate comprising applying a precursor of said electrocatalytic or protective coating to the surface of said metal substrate, decomposing said precursor by means of a thermal treatment, characterized in that said thermal treatment is carried out on all or part of the surface of the metal substrate by means of a hot air jet coming from a gun or a blower.
2. The method of claim 1 wherein the metal of said substrate is a valve metal.
3. The method of claim 1 wherein said precursor contains a corrosion inhibitor
4. The method of claim 1 wherein said catalytic coating comprises at least one metal or metal oxide selected from the group consisting of Pt, Ir, Os, Pd, Rh, Ru and oxides thereof.
5. The method of claim 3 wherein said corrosion inhibitor comprises at least one metal or metal oxide selected from the group consisting of Ti, Ta, Zr, Nb, Si, Al and oxides thereof.
6. The method of claim 1 characterized in that the temperature of the metal substrate is controlled by an infrared system for local measurement.
7. The method claim 1 characterized in that the temperature of the metal substrate is controlled by a thermocouple for local measurement.
8. The method of claim 1 characterized in that the metal substrate is an exhausted electrode structure.
9. The method of claim 8 characterized in that the metal substrate is the flange of an electrochemical cell.

10. The method of claim 1 characterized in that said part of the surface of the metal substrate is a damaged area previously provided with a coating.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 98/04270

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C25B11/00 C23C18/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C25B C23C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
E	WO 98 38351 A (THE WHITAKER CORPORATION) 3 September 1998 see page 10; claims 1,2,4	1,4
X	PATENT ABSTRACTS OF JAPAN vol. 016, no. 372 (E-1246), 11 August 1992 & JP 04 119615 A (MATSUSHITA ELECTRIC IND CO LTD), 21 April 1992 see abstract	1
A	GB 2 067 537 A (ORONZIO DE NORA IMPIANTI ELETTROCHIMICI S.P.A.) 30 July 1981 see page 2, line 18 - page 3, line 26	1

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

19 November 1998

Date of mailing of the international search report

26/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3018

Authorized officer

Groseiller, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/04270

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9838351 A	03-09-1998	NONE	
GB 2067537 A	30-07-1981	BR 8008411 A	14-07-1981
		CH 651073 A	30-08-1985
		DE 3048077 A	10-09-1981
		FR 2472036 A	26-06-1981
		IN 154704 A	08-12-1984
		JP 1041714 B	07-09-1989
		JP 1559433 C	16-05-1990
		JP 56119787 A	19-09-1981
		SE 501077 C	07-11-1994
		SE 8008711 A	21-06-1981
		US 4395436 A	26-07-1983